

Abstract

A method of producing a washcoated monolith catalyst
utilizing a dual sol binder system, wherein the binder
system is a blend of an alumina sol and a silica sol and
5 wherein the ratio of the alumina to the silica in the dual
sol binder system is from about 6:1 to about 1:3.

SRC:dg
C:\WP\PAT\P1049
8-21-01
93789